



# TECHNICAL DATA SHEET

**PRODUCT: CALCIUM CARBONATE MASTERBATCH**

**GRADE: MF550**

ITEM	CACO3 CONTENT	CACO3 PARTICLE SIZE	MELT TEMPERATURE	MELT MASS FLOW RATE		BULK DENSITY	MOISTURE	PELLET SIZE	PROCESSING TEMPERATURE	APPLICATION	AVERAGE USAGE
TEST METHOD	ASTM D5630		DSC	ASTM	D1238	ASTM D1895	ASTM D6980				
UNIT	%	micron	OC	°C; kg	g/10 min	g/cm3	%	mm	°C		%
STANDARD	81.5 (±2)	3.0 (± 0.2)	145	230; 2.16	5.0 (± 3)	1.25 (± 0.2)	<0.1	3~4	145 ~ 280	PP Fiber	40

## Attention

*The data is of a consultative based on our experience.*

*The quality of the final product depends on the technical parameters and control parameters during the production process.*

## A DONG PLASTIC JOINT STOCK COMPANY

HO: No. 30/64 Ly Ai Street, Song Phuong, Hoai Duc, Ha Noi, Viet Nam.

Hanoi Office: No. 14-15, A18-BTSL2, Le Trong Tan str., An Khanh, Hoai Duc, Hanoi, Vietnam.

Factory: Rd. D1, Yen My II Industrial Zone, Yen My, Hung Yen, Vietnam.

E: [info@adcplastic.com](mailto:info@adcplastic.com) | W: [adcplastic.com](http://adcplastic.com)

T: +84 243 365 8245 | F: +84 243 321 3268